



TECHNICAL SPECIFICATION TIGHT-HEAD STEEL DRUM

STANDARDS : TS EN ISO 15750-2

DIMENSIONS : See the technical drawing.

Volume	Body		Ends		Weight	UN Approval (Optional)
	Thickness	Tolerance	Thickness	Tolerance		
216.5 Lt.	0.70 mm.	± 0.06 mm.	0.80 mm.	± 0.07 mm.	13.4 Kg.	1A1/Y1.8/200
216.5 Lt.	0.70 mm.	± 0.06 mm.	0.90 mm.	± 0.08 mm.	13.9 Kg.	--
216.5 Lt.	0.70 mm.	± 0.06 mm.	1.00 mm.	± 0.08 mm.	14.4 Kg.	--
216.5 Lt.	0.80 mm.	± 0.06 mm.	0.80 mm.	± 0.07 mm.	14.7 Kg.	1A1/X1.2/250
216.5 Lt.	0.80 mm.	± 0.06 mm.	0.90 mm.	± 0.08 mm.	15.2 Kg.	1A1/X1.2/250
216.5 Lt.	0.80 mm.	± 0.06 mm.	1.00 mm.	± 0.08 mm.	15.7 Kg.	1A1/X1.2/250
216.5 Lt.	0.90 mm.	± 0.07 mm.	0.90 mm.	± 0.08 mm.	16.5 Kg.	1A1/X1.2/250
216.5 Lt.	0.90 mm.	± 0.07 mm.	1.00 mm.	± 0.08 mm.	17.0 Kg.	1A1/X1.2/250
216.5 Lt.	1.00 mm.	± 0.07 mm.	1.00 mm.	± 0.08 mm.	18.3 Kg.	1A1/X1.2/250
216.5 Lt.	1.00 mm.	± 0.07 mm.	1.20 mm.	± 0.08 mm.	19.4 Kg.	--
216.5 Lt.	1.20 mm.	± 0.08 mm.	1.20 mm.	± 0.08 mm.	21.9 Kg.	--
216.5 Lt.	1.30 mm.	± 0.08 mm.	1.30 mm.	± 0.08 mm.	23.8 Kg.	--

Material and Production Specifications:

Body is electrically seam welded. Two beads are formed on the body. Body and ends are seamed by 7-layered seaming technique (triple seam) and seaming compound is applied to the seaming line prior to seaming operation.

Corrugations are formed between the beads and the ends for extra resistance at the corrugated types.

Steel : Cold Rolled Steel (EN 10130 and EN 10131)

Closures : 2" and ¾" closures and cap-seals. (TS EN ISO 15750-3)

External Paint : Exterior of the drum is finished with oven-drying enamel as per customer preference.
Dry film thickness for body : 18 microns min.
Dry film thickness for ends : 25 microns min.
Gloss for paint : 60 Gloss min. (with 60° Glossmeter)

Interior Coating (Optional) : Interior of the drum is lined with with foodgrade epoxy phenolic lacquer.
Dry film thickness : 7 microns min.

Marking : Production date and manufacturer name are coded on the lower side of the body with ink-jet system. Any other coding can be made with silk-screening system on the body or top-end of the drum.

Tests : All in process and final product tests are undertaken according to ISO 9001:2000 Quality Management System and test results are informed to the customer by Quality Reports. All the drums are 100% leak tested.



İZVAR AMBALAJ SANAYİ VE TİCARET A.Ş.

Merkez : Acarlar İş Merkezi F-Blok K3 No 10 Kavacık 34805, Beykoz İstanbul
Tel: ++ 90 216 6802080 Faks: ++ 90 216 6802090
Fabrika : Tavşantepe Sk. No 74 Pelitli 41490, Gebze Kocaeli
Tel: ++ 90 262 7510220 Faks: ++ 90 262 7510221

www.izvar.com

